Performance Testing

For affordable pre-painted steel we trust UniCote® Steel. UniCote® is tested and manufactured to withstand the harshest Australian conditions. UniCote® is backed by a strong warranty, so you know it's made to last.



Heat Resistance

Suitable for continuous service up to 100°C. Continuous service at higher temperatures may cause some colour change and damage to the paint film.



Scratch Resistance

Good scratch resistance. Testing includes needle scratch test - no marking of paint surface when a needle with up to a 2kg weight attached is drawn across. AS 2331.4.7.



Salt Spray

Meets the requirements of AS/NZS2728:2013.



Humidity Resistance

Meets the requirements of AS/NZS2728:2013.



Bend Test

No loss of adhesion or paint cracking when bent around a diameter equal to five times the thickness of the sheet.



Impact Resistance

No loss of paint adhesion after a test piece is struck on the reverse side with a specified force, in line with the test methodology.



QUV Resistance (durability of coating system)

Meets the requirements of AS/NZS2728:2013.

Note: Tests are conducted on a flat panel.

Colour Chart

Whether your home is classic or modern, you will find the perfect colours to suit your home with our CorroForm™ and RibForm™ colour range. Choose from any of the 22 available colours below.



Note: All colours shown above are indicative only. Slight variations may occur from the pre-painted metal. Equivalent colour names listed are trademarks of BlueScope Steel Limited and used only for comparison. The use of colour names in any Rollsec document indicates no more than the colour of the product supplied or a colour equivalency.

Where strength matters